

XOANONS® Anti-graffiti and easy-cleanability leveling agent

Model number

XOANONS®WE-D9542N

Composition

silicone modified polyacrlate with hydroxy group

Specifications

Model number	Appearance	Softening point	hydroxyl value (mg KOH/g)
XOANONS®WE-D9542N	Slight yellowish solid	100-110°C	100-130

Application system

Hydroxyl acrylic powder coating/paint

Incorporation

Premix with resin, cure agent, pigment, filling and other additives, then melt together.

Suggested addition

Model number	Addition to total formulation%
XOANONS®WE-D9542N	1-20(adjusted by anti-fouling request)

Property and advantage

Model number	Property and advantage
XOANONS®WE-D9542N	Suit for hydroxyl acrylic powder coating. Use blocked isocyanate or amino resin as cure agent. Improve surface anti-graffiti and cleanability. Oil pen can wipe repeatedly. Excellent performance of resistance of oil-pen wipe, blocking resistance, hydrophobicity and oleophobicity. Prolong bake time to improve anti-graffiti property.

Package

5KG 15KG

The container should be closed tightly before completely use up.

Storage

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above mentioned statements have to be adjusted to the circumstances of the processor.



Should store in cool and dry place.

Can keep intact 24 months in original package.