

## XOANONS® Adhesion additives

### Model number

XOANONS®WE-D322

### Composition

Epoxy group silicane compound

### Specifications

Model number	Appearance	Solvent	Density g/ml (25±1 °C)	Viscosity(s) (25±0.2 °C)	Content(%) (105 °C 3h)
XOANONS® WE-D322	Transparent clear liquid	—	1.05-1.09	7-15 (T-4 viscometer)	≥95

### Application system

Solvent based coating/paint Ink

### Addition

Model number	Addition to total formulation (%)
XOANONS®WE-D322	1.0-2.0

### Incorporation

XOANONS®WE-D322 should be added in the alkyd resins in alkyd+TDI systems.

### Property and advantage

Model number	Property and advantage
XOANONS®WE-D322	XOANONS®WE-D322 can increase the adhesion of coatings with glass substrate and improve the water&salt-fog resistance of coatings. It is suitable for two-pack systems

### Package

25KG/180KG

The container should be closed tightly before completely used up

### Storage

Should store in cool and dry place

Can keep intact 24 months in original package

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above mentioned statements have to be adjusted to the circumstances of the processor.