

XOANONS® Silicon free defoamer

Model number

XOANONS®WE-D930

Composition

Organic silicon free foam breaking polymer solution

Specifications

Model number	Appearance	Solvent	Density g/ml (25±1℃)	Viscosity (25±0.2℃)	Content(%) (140℃ 2h)
XOANONS®WE-D930	Yellowish translucent viscosity liquid	—	0.98-1.02	≥Z3 (Bubble viscometer)	≥95

Application system

Solvent based coating/paint and Ink

Addition

Model number	Addition to total formulation (%)
XOANONS®WE-D930	0.1-0.5

Incorporation

Should be added to the mill base for improve the foam-inhibition, deaeration and defoaming speed of the system

Property and advantage

Model number	Property and advantage
XOANONS®WE-D930	Excellent foam-inhibition and deaeration ability without side-effect. Can be used in acrylic, polyester, epoxy systems except varnish. Precipitation may occur at long time storage for the exist of hydrophobic particles. It does not affect the quality of products after stirring before use. Be attention that the shelf-time would be 1-2 days after thinning.

Package

25KG/180KG

The container should be closed tightly before completely used up



Storage

Should store in cool and dry place

Can keep intact 24 months in original package